



Iso-Flex® 760 Intermediate Coat

PRODUCT DESCRIPTION

Iso-Flex 760 Intermediate Coat is a two-component, high solids, chemically curing, polyurethane coating. It cures quickly to a high durometer, tough elastomer that bonds continuously to concrete or a base membrane. Iso-Flex 760 Intermediate Coat has a low viscosity, and effectively encapsulates small aggregates to provide a tough, durable wear coarse for vehicular traffic. The thickness and aggregate loading will be dependent upon the service conditions.

BASIC USES

Typical application of Iso-Flex 760 Intermediate Coat is as a wear course when installing the Iso-Flex 760 Coating Systems in areas of parking structures, stadiums, loading docks, etc. that are exposed to severe traffic conditions. The product may also be used as a patching compound prior to applying Iso-Flex 750 Base Coat.

ADVANTAGES

- Iso-Flex 760 Intermediate Coat develops a continuous bond to Iso-Flex Base Coat.
- The product remains flexible over a wide temperature range.

LIMITATIONS

- Iso-Flex 760 Intermediate Coat must be applied to clean, dry, freshly cured Iso-Flex Base Coat or a primed substrate.
- The work life is fairly short, therefore the application must be tightly scheduled and applied by trained, skilled personnel.

PACKAGING

Iso-Flex 760 Intermediate Coat is available in 5 gallon containers.

STANDARD COLOR

Concrete Gray

INSTALLATION

Iso-Flex 760 Intermediate Coat must be installed over freshly cured Iso-Flex Base Coat or freshly primed concrete. The Iso-Flex 760 Intermediate Coat is quickly spread by squeegees and rollers to the correct wet millage, and then saturated to excess with approved aggregate.

PRECAUTIONS

To ensure safe installation of Iso-Flex 760 Intermediate Coat, please refer to the Material Safety Data Sheets that accompany each product shipment.

TECHNICAL DATA FROM LABORATORY TESTS

(Field Properties May Vary)

Property	Test Method	Test Result
Weight per Gallon		9.2 lbs/gal
Hardness (Shore A)	ASTM D2240	80-90
Viscosity @ 77°F(25°C)	ASTM 2196 #4 RVT @ 20 rpm	1000-2000 cps
Flash Point	ASTM D93	> 200°F (93°C)
Cure Time @ 77°F(25°C)	ASTM C920	6-8 hours
Weathering Resistance	ASTM G53-83	Yellowing
Tensile Strength	ASTM D412	2000 psi
Ultimate Elongation	ASTM D412	150%
Tear Resistance	ASTM D1004	180 pli
% Yield (Wet→Dry)		99%
Pot Life @ 77°F(25°C)	ASTM C603	25-30 minutes
Shelf Life @ 77°F(25°C) (in sealed containers)		6 months

WARRANTY

LymTal warrants that its products are manufactured free of defects and conform to the technical data listed. Under this warranty we will replace, at no charge, any material proven defective when applied in accordance with our written instructions for applications recommended by us as suitable for subject product. LymTal shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use of the product.

Revised: 03/2013

LymTal International, Inc.

4150 South Lapeer Road • Lake Orion, MI 48359 • Tel (248) 373-8100 • Fax (248) 373-3480 • www.lymtal.com