

Iso-Flex[®] Balcony & Walkway Coating System

PRODUCT DESCRIPTION

Iso-Flex Balcony systems are cold, liquid applied, urethane elastomeric deck coating membranes with integral, urethane, skid resistant toppings that are designed for use under direct exposure to pedestrian traffic. All Iso-Flex deck coating systems are attractive and durable, and are designed to protect the deck surface from water and/or chloride penetration.

The Iso-Flex Balcony system consists of one-part elastomeric urethane membrane bonded continuously to the substrate for protection against water damage, and one or more urethane traffic topping coats with encapsulated aggregate for skid resistance. Recommended mil thickness of the systems will vary depending upon intended service conditions.

BASIC USES

Applications for Iso-Flex Balcony coating systems include a wide variety of surfaces that will be subject to pedestrian traffic such as balconies, walkways, mechanical rooms, etc. Other applications may include laundry rooms, kitchens or any facilities where waterproof surfaces are desirable.

ADVANTAGES

- The Iso-Flex Balcony coating system can be applied with a two-step process, enabling rapid turn around and minimal inconvenience.
- The Iso-Flex Balcony coating system is impervious to water and/or chloride penetration and, with aliphatic top coat materials, is color-fast even in severe UV exposure.
- Adhesion promoters in the base coat material eliminate the need for priming in most applications. Adhesion tests are recommended prior to application.

TECHNICAL DATA FROM LABORATORY TESTS			
<i>(Field Properties may Vary)</i>			
Property	Test Method	780 Base Coat	750 AL Top Coat
Weight		9.3 lbs/gal.	9.0 lbs/gal.
Hardness (Shore A)	ASTM D2240	60-70	80-90
Viscosity @ 77°F(25°C)	ASTM D2196 #4 RVT @ 20 rpm	3000-6000 cps	1500-3000 cps
Flash Point	ASTM D93	110°F (43.3°C)	110°F (43.3°C)
Cure Time @ 77°F(25°C)	ASTM C920	24 hours	24 hours
Abrasion Resistance	ASTM D4060 Tabor 1000 rev CS17 Wheel, 1000 grams	Loss 0.01 grams	Loss 0.03 grams
Weathering Resistance	ASTM G53-83	Yellowing	No Visual Effect
Permeability	ASTM E398	1.6 perms	1.6 perms
Peel Adhesion	ASTM C794	30 pli	n/a
Tensile Strength	ASTM D412	1200 psi	2500 psi
Ultimate Elongation	ASTM D412	600%	100%
Tear Resistance	ASTM D1004	80 pli	200 pli
% Yield (Wet→Dry)		86%	80%
Pot Life @ 77°F(25°C)	ASTM C603	1 hour	1-2 hours
Shelf Life @ 77°F(25°C)	(in sealed containers)	6 months	6 months
Chemical Resistance	No effect on System from Common Oils, Salts, Alkalis, Motor Oil, Anti-Freeze, Gasoline, Mineral Spirits.		

LIMITATIONS

- Iso-Flex Balcony coating system is designed for application in relatively thin mil film thicknesses.
- The coating develops a chemical bond to the primed substrates to which it is applied. Curing agents, form releases, sealers, etc., may interfere with good adhesion. Therefore, surfaces to receive the product should be free of these and other potential contaminants. Concrete slabs should be water cured or cured with compatible curing compounds approved by the manufacturer. Surface bond tests are recommended to determine possible need for primers.
- Application must be to clean, sound, dry substrates at temperatures above 40° F (5° C).
- Adequate ventilation must be provided, as recommended by the manufacturer.

PACKAGING

Iso-Flex Base Coat and Top Coats are available in 5 and 53 gallon containers.

STANDARD COLOR

Concrete Grey (*See color chart for other standard colors*)

INSTALLATION

Preliminary: Surfaces to receive the Iso-Flex coating system must be clean, dry, sound, relatively smooth and free of voids, ridges and sharp projections. New concrete surfaces should be water cured or cured with compatible curing compounds.

Surface Preparation: Shotblasting where possible will provide a sound, clean substrate. In areas where shotblasting is not feasible, sandblasting, or power washing with a spinner or turbo tip is recommended.

	<u>MVT</u>	<u>HVT</u>
Base Coat	20 mils	20 mils
780 Base Coat		
Wear Course I	15 mils	15 mils
750 TCAL		
Sand (16/30 grit)	6-8 lbs/100 ft ²	10 lbs/100 ft ²
Wear Course II		15 mils
750 TCAL		
Sand (16/30 grit)		10 lbs/100 ft ²
Total	35 mils	50 mils

* System millages are dry film thicknesses.

Detailing: Joints or cracks should be pretreated prior to general application by grinding out and sealing or overbanding with compatible Iso-Flex products, as recommended. Terminations and penetrations should also be sealed prior to general application.

Application: The Iso-Flex coating system must be applied in accordance with manufacturer's specific recommendations.

PRECAUTIONS

To ensure safe installation of the Iso-Flex coating system, please refer to the Material Safety Data Sheets (MSDS), that accompany each product shipment.

WARRANTY

LymTal warrants that its products are manufactured free of defects and conform to the technical data listed. Under this warranty we will replace, at no charge, any material proven defective when applied in accordance with our written instructions for applications recommended by us as suitable for subject product. LymTal shall not be liable for any injury, loss or damage, direct or consequential, arising out of the use of the product.

Revised: 10/07

LymTal International, Inc.

4150 South Lapeer Road • Lake Orion, MI 48359 • Tel (248) 373-8100 • Fax (248) 373-3480 • www.lymtal.com